



**Plus 8  
Grit-o'Cob®**

**DERIVED FROM THE WOODY PORTION OF THE CORN COB**

<b>PARTICLE SIZE DISTRIBUTION - SCREEN ANALYSIS</b>						
U.S. Standard Mesh				Typical	Minimum	Maximum
Pass	Retained			%	%	%
-	3.5			1	0	2
3.5	4			4		
4	6			30		
6	8			65		
8	10			5		
10	-10			0.9	0	1

<b>SUMMARY OF PHYSICAL PROPERTIES</b>			
Moisture, maximum %	10	Resistance to attrition, %	>98.6
Loose bulk density, lb/ft <sup>3</sup>	18 - 24		

This information was derived from analytical and experimental data generated by The Andersons and supplemented by data obtained from manufacturers using various corn cob products in a variety of applications. For properties not listed and specific to your use, contact The Andersons Corn Cob Products.

*Revised July 2013D*

**Grit-o'Cob** is a registered trademark of The Andersons.